



Americrete, Inc.
41730 Reagan Way
Murrieta, Ca 92562
Toll Free (800) 775-8880
Technical Help (800) 775-8880

Material Safety Data Sheet A-1800

Emergency Assistance

For Chemical Emergency Spill, Leak, Fire or Exposure call 24 hours a day: CHEMTREC (800) 424-9300. Outside U.S. call (703) 527-3887. Collect calls accepted.

SECTION I PRODUCT IDENTIFICATION

Product Name: Release A-1800
Product Class: Solvent Naphtha (Petroleum), Medium Aliphatic
C.A.S. Number: 64742-88-7
HMIS Rating: Health 2 Fire 2 Reactivity 0
0=Least, 1=Slight, 2=Moderate, 3=High, 4=Extreme

SECTION II INGREDIENTS

A complex combination of predominantly hydrocarbon

SECTION III PHYSICAL DATA

Appearance: Clear, Colorless Liquid
Odor Characteristic: Light Hydrocarbon Odor (optional bubblegum, grape, floral, citrus, or mint)
Specific Gravity: 99
Vapor Density: 3.5
Solubility in Water: Negligible
Volatility %: 55%
Evaporation Rate: .1

SECTION IV FIRE AND EXPLOSION HAZARD DATA

Flammability Class:

FlashPoint: >145° F
LEL: 1%
UEL: Unknown
Extinguishing Media: Water, CO2 or Dry Chemical
Auto-Ignition Temperature: Approx. 880 Degrees F.

Basic Fire-fighting Procedures:

- Use water spray, dry chemical, alcohol foam, all purpose AFFF or carbon dioxide to extinguish fire. Evacuate area and fight fire from a safe distance.

Handling and Storage: Avoid hot metal surfaces. Use in cool well ventilated areas. Kep containers closed when not in use. Keep away from open flames and excessive heat. Use non-sparking itmes when using this material.
Other precautions: Smoking in areas where this material is used should be strictly prohibited.

REGULATORY INFORMATION

Transportation: Not regulated by US DOT in containers of less than 110 gallons.

DOT Classification: "Combustible Liquid NOS/Combustible/NA-1993/Pgill/Petroleum Distillates/Petroleum Paphtha"

The information herein is general to assist our customers in determining whether our products are suitable for their specific applications. Our products are intended for sale to commercial and industrial customers. We require that customers should inspect and test our products before use to satisfy themselves as to the content and suitability for the applications they intend to use our products for. **Nothing herein shall constitute any warranty expressed or implied, including any warranty of merchantability or fitness for a particular purpose**, nor is any protection from any law or patent to be inferred. The exclusive remedy for all proven claims is replacement of our materials and in no event shall we be liable for incidental consequential damages.