



Americrete, Inc.
41730 Reagan Way
Murrieta, Ca 92562
Toll Free (800) 775-8880
Technical Help (800) 775-8880

Material Safety Data Sheet A-650

Emergency Assistance

For Chemical Emergency Spill, Leak, Fire or Exposure call 24 hours a day: **CHEMTREC** (800) 424-9300. Outside U.S. call (703) 527-3887. Collect calls accepted.

SECTION I PRODUCT IDENTIFICATION

Product Name: Gray Asphalt Resurfacer with Self Levelers A-650
Product Class: Proprietary Co-Polymers & Aggregates mixed with Silica Sand & Cement
C.A.S. Number:
HMIS Rating: Health 1 Fire 0 Reactivity 0
0=Least, 1=Slight, 2=Moderate, 3=High, 4=Extreme

SECTION II PHYSICAL DATA

Appearance: Cement
Odor Characteristic: Ester/acetic odor
Specific Gravity: 3.10
Vapor Density: N/A
Solubility in Water: Dilatable
Volatility %
Evaporation Rate: N/A

SECTION III FIRE AND EXPLOSION HAZARD DATA

Flammability Class: N/A
Flash Point: N/A
LEL: N/A
Extinguishing Media Water, CO2 or Dry Chemical
Unusual Fire and Explosive Procedures: Wear self-contained breathing apparatus

SECTION IV HEALTH HAZARD DATA

Permissible Exposure Level: The ACGIH TLV and OSHA PEL for vinyl acetate are both set at 100 ppm for an 8 hour TWA and at 20 ppm for the STEL

Effects of Overexposure:

- Inhalation Headache, nausea, irritation of the nose, throat and lungs, vomiting
- Skin Contact may cause slight irritation

California Prop 65: This product contains trace amounts of a component or components known to the state of California to cause cancer: Acrylamide (79-06-1) <0.1%, and Acetaldehyde (75-07-0) <0.1%

The information herein is general to assist our customers in determining whether our products are suitable for their specific applications. Our products are intended for sale to commercial and industrial customers. We require that customers should inspect and test our products before use to satisfy themselves as to the content and suitability for the applications they intend to use our products for. **Nothing herein shall constitute any warranty expressed or implied, including any warranty of merchantability or fitness for a particular purpose**, nor is any protection from any law or patent to be inferred. The exclusive remedy for all proven claims is replacement of our materials and in no event shall we be liable for incidental consequential damages.