



Product Information

Americrete A-63,000 SPECIFICATION

Vapor Seal – Moisture Control System

Surface Preparation - MANDATORY

Concrete substrate must be shot blasted or grinded before application of Vapor Seal in order to open the pores and remove the top shell of the concrete substrate. This will also remove all existing coatings, sealers, curing agents or any foreign material. There is no warranty if this step is not executed properly.

Crack Repair

If cracks are present, V-grind all cracks with a crack chaser to open the cracks to approximately 1/2" wide. Use Americrete's A-7300 Crack Repair Paste by mixing equal parts of component A with component B. Apply in cracks with a putty knife and allow to dry. Shave the excess epoxy paste flush with the existing concrete substrate using a razor blade.

Perform Moisture Readings

Perform Moisture Readings on the concrete substrate: Calcium Chloride Test and a PH test. The readings should not be above 12 pounds per square foot and PH readings should be neutral, at 7.

Mixing Instructions

Vapor Seal is a 1.5 gallon kit containing two components with a 2 to 1 ratio. Mix 2 parts component A with 1 part component B and thin material with 2 quarts of water or acetone per kit.

Installation Procedures

Using a 3/8" nap roller, coat the entire floor with Americrete's A-6300 Vapor Seal thin out first application. Allow to dry.

Repeat step for second coat. Allow to dry.

NOTE: If a concrete coating is to be applied over vapor seal while second application is wet broadcast 30 silica sand over entire area to refusal.

Product Warranty/Liability Disclaimer

Since no control is exercised over product use, AMERICRETE represents and warrants ONLY that the products are of consistent quality within manufacturing tolerances for a period of ONE year. NOTE: if Americrete sealers are not used to seal the surface then there is NO WARRANTY implied. Americrete sealers must be applied to the substrate for Americrete to warranty material.

All sales are final. NO other oral or written representation or statement of any kind, expressed or implied, now or hereafter is authorized or warranted by AMERICRETE including those of marketability or

fitness for a particular purpose. Liability for breach of contract, negligence or on any other legal basis is limited to the lesser cost of refund or replacement of material proven to be defective. AMERICRETE, will not be liable for special, incidental or consequential damages, including for delays or lost profits. There is no warranty for product installations, color variations, product delamination or cracks in the surface due to the substrate cracking. The end user shall determine the suitability of the products for the intended use and assumes all risks and liability in connection therewith. NOTE: If litigation arises the party filing the complaint or law suit will be responsible for all attorney fees and court costs incurred by AMERICRETE, and all other costs related to the investigation of the law suit and/or complaint.

This warranty is effective August 1, 2007, and supersedes any and all previous warranties, written or verbally communicated Note: Americrete products are to be applied only when surface temperatures are at 55 degrees or higher. Do not apply when rain or other precipitation is expected within 24 hours.

A five year warranty is available only if requested and Must be written signed and "notarized" by an Americrete officer.