



**Americrete W-90,000
SPECIFICATION**

Wall Stamp

Description

This specification includes resurfacing methods used for applying a decorative Stamp overlay over vertical surfaces including block, stucco and drywall to give the surface the appearance of rock.

Surface Preparation

Before applying Americrete Wall Stamp System over brick, block, concrete, stucco, siding, drywall, or any other vertical surface the area to be coated must be scraped, and cleaned. Any loose debris must be removed.

Mixing Procedures

Mix Americrete Wall Stamp W-8300 with 3 3/4 to 4 quarts of water to achieve the desired consistency.

Application

Note: W-8000 Primer and a scratch coat must be applied to every application. Only water needs to be added to W-8300 Wall Stamp.

Scratch Coat

On a clean dry surface apply W-8000 bonder to the substrate by using a paint roller at a rate of 250 to 300 square feet per gallon. Apply Americrete Wall Stamp W-8300 at a rate of 80 feet per bag into wet primer.

NOTE: All seams and joints are to be repaired with A-1620 mesh tape and bonder and 8300 wall stamp.

1. Apply second bonder coat to the surface DO NOT allow to dry.
2. Apply Wall Stamp W-8300 mix at a rate of 25 square feet per 1/4" mix using a hawk and trowel directly into the wet bonder.
3. Spray Americrete Liquid Release A-1800 to the surface, and stamp your pattern.
4. Staining can be done while cement is wet or dry.
5. Carve for desired look, and seal. Please see Sealers below for more information.
6. SEALERS:

Apply two coats of A-1300 or A-1325 satin finish to the finished product. Other Americrete sealers can be applied depending on the look or gloss.

Product Warranty/Liability Disclaimer

Since no control is exercised over product use, AMERICRETE represents and warrants ONLY that the products are of consistent quality within manufacturing tolerances for a period of ONE year.

NOTE: if Americrete sealers are not used to seal the

surface then there is NO WARRENTY implied. Americrete sealers must be applied to the substrate for Americrete to warranty material.

All sales are final. NO other oral or written representation or statement of any kind, expressed or implied, now or hereafter is authorized or warranted by AMERICRETE including those of marketability or fitness for a particular purpose. Liability for breach of contract, negligence or on any other legal basis is limited to the lesser cost of refund or replacement of material proven to be defective. AMERICRETE, will not be liable for special, incidental or consequential damages, including for delays or lost profits. There is no warranty for product installations, color variations, product delamination or cracks in the surface due to the substrate cracking. The end user shall determine the suitability of the products for the intended use and assumes all risks and liability in connection therewith. NOTE: If litigation arises the party filing the complaint or law suit will be responsible for all attorney fees and court costs incurred by AMERICRETE, and all other costs related to the investigation of the law suit and/or complaint.

This warranty is effective August 1, 2007, and supersedes any and all previous warranties, written or verbally communicated Note: Americrete products are to be applied only when surface temperatures are at 55 degrees or higher. Do not apply when rain or other precipitation is expected within 24 hours.

A five year warranty is available only if requested and Must be written signed and "notarized" by an Americrete officer.