



Americrete^{Inc}
MANUFACTURER OF DECORATIVE OVERLAYS & SEALERS

A-18,000
Asphalt Resurfacer

Description

This specification provides an economical alternative to the replacement of existing asphalt. The system creates a flexible and durable finish that can be used to re-grade, re-level, renovate, resurface and add slip resistance with or without pigmented color. The new finish will resist petroleum products, oils, water, salts, freeze-thaw cycles and ultra violet rays. Americrete's **A-650 Asphalt Resurfacer** over asphalt will eliminate messy oils and create a finish that is environmentally safe and easy to use.

Surface Preparation

Oil, grease and other petroleum products should be removed by degreasing the surface with **A-100 Degreaser**. Broom **A-100 Degreaser** over surface and allow to set for 30 minutes. Rinse with a water hose and then power wash the surface. Repeat process as needed to remove contamination. **Severe areas may have to be removed and replaced if contamination is the full depth of the asphalt.**

Crack Repair

All loose existing asphalt shall be removed from the cracks and are to be repaired with **AR-625 Asphalt Spall Repair**. Repaired cracks must be dry before proceeding with application. **A-1600 Flex Mesh** and **A-650 Asphalt Resurfacer** can be applied over repair areas to be reinforced, and stabilize the crack if necessary.

Application Procedure

1. Use **A-100 Degreaser** at a rate of 200 to 300 square feet per gallon. Degrease the asphalt by applying the **A-100 Degreaser** with a broom. Allowing to set for 30 to 60 minutes, hose off and then power wash the surface to remove all residue.
2. Fill low areas and large cracks with **AR-625 Asphalt Spall Repair** by mixing one-gallon of **AR-375 Admix** plus ½ quart water at a time (not to exceed 2 quarts) until desired consistency is achieved to one bag of **AR-625 Asphalt Spall Repair**. **Note: For larger spalls, a larger aggregate may need to be added to the mix. Contact an Americrete Representative for product information.**

3. Mix 6 to 6 ½ quarts of water to one bag of **A-650 Asphalt Resurfacer**. Allow to dry and apply a 2nd coat to area. Application can be done by either a squeegee or asphalt resurfacing truck.
4. Allow it to dry two to four hours before allowing vehicular traffic.
5. **Note: AR-650 Asphalt Resurfacer can be tinted with powder only, no liquid colorants.**
6. **Note: The surface must be sealed with AR-1000 Black Stain or A-1200RS Clear, Natural Seal. These are both water base, non-hazardous sealers.**

Note: Do not apply product over new or freshly treated asphalt. Must use AR-650 Black Asphalt Resurfacer when going over asphalt.

Product Warranty:

Americrete, Inc. blends its products to the highest quality. Warranty does not apply to any persons, company or private individuals who have not attended an Americrete, Inc. training class and/or have not been approved as a Certified Applicator of Americrete, Inc. products. This warranty is limited to the replacement of material (product) for a period of 1 year for single product application and for a period of 5 years for entire system application only if the maintenance has been performed as stated above and the product(s) have been proven to be defective. Product must be applied to manufacturer's specifications, and over a sound substrate. There is no warranty for cracking, damage to substrates or replacement of any tangible items. This warranty, dated October 2004, supercedes all previous warranties.

Note: Americrete products are to be applied only when surface temperatures are at 55 degrees or higher. Do not apply when rain or other precipitation is expected within 24 hours.