



This specification includes resurfacing methods used for applying a decorative coating over vertical surfaces.

Note: W-8000 Primer and a scratch coat must be applied to every application. Only water needs to be added to W-8300 Wall Stamp.

Surface Preparation

Before applying **Americrete Wall Stamp System** over brick, block, concrete, stucco, siding, drywall, or any other vertical surface the area to be coated must be scraped, and cleaned. Any loose debris must be removed.

Mixing Procedures

Mix **Americrete Wall Stamp W-8300** with 3 3/4 to 4 quarts of water to achieve the desired consistency.

Application

Note: Always follow surface preparation before coatings are applied.

1. On a clean dry surface **Americrete Wall Stamp Primer W-8000** is to be applied by using a paint roller over the entire surface to be coated at a rate of 100 to 300 square feet per gallon. Apply **Americrete Wall Stamp Primer W-8000** at a rate of 20 square feet at any one time to prevent the product from drying before the **Americrete Wall Stamp W-8300** is applied.
2. Apply scratch coat mix to the surface at a rate of approximately 200 square feet per mix using a pool trowel. Allow it to dry.
3. Apply second primer coat to the surface. Following the step one procedure.
4. Apply **Wall Stamp W-8300** mix at a rate of 25 square feet per 1/4" mix using a hawk and trowel.
5. Spray **Americrete Liquid Release A-1800** to the surface, and stamp your pattern.
6. Staining can be done while cement is wet or dry.
7. Carve for desired look, and seal. Please see **Sealers** below for more information.

Sealers

Allow finished surface to dry for a minimum of 24 hours. For indoor or cool area application, you may need to wait 48 hours. The dry, cured surface can now receive 2 finishing coats of **Americrete Concrete Seal A-1300, A-1325 Satin Finish, A-1330 Enviro Seal Satin Finish, A-1350 Concrete Shield** or **A-5500 Water Base High Shine**.

Americrete Concrete Sealers should be applied using a pump sprayer and a broom in two lightly sprayed applications. Allow the first application to dry thoroughly prior to the second application.

Product Warranty:

Americrete, Inc. blends its products to the highest quality. Warranty does not apply to any persons, company or private individuals who have not attended an Americrete, Inc. training class and/or have not been approved as a Certified Applicator of Americrete, Inc. products. This warranty is limited to the replacement of material (product) for a period of 1 year for single product application and for a period of 5 years for entire system application only if the maintenance has been performed as stated above and the product(s) have been proven to be defective. Product must be applied to manufacturers specifications, and over a sound substrate. There is no warranty for cracking, damage to substrates or replacement of any tangible items. This warranty, dated October 2004, supercedes all previous warranties.

Note: Americrete products are to be applied only when surface temperatures are at 55 degrees or higher. Do not apply when rain or other precipitation is expected within 24 hours.